

TDS updated 03/2023

PHACT™ CA8270P-B1

PHACT CA1270P-B1 is an environment-friendly semi-crystalline bio polymer which has excellent biodegradability. It is a compounded polymer with Polylactic acid and Amorphous polyhydroxyalkanoate. PHACT CA1270P-B1 is appropriate for blown film process to produce film applications.

PROPERTIES OF PHACT CA8270P-B1

| Properties | | Units | ASTM No | CA8270P-B1 |
|--|----|----------|---------|------------|
| Forms | | - | | Pellet |
| Specific Gravity | | - | D792 | 1.23 |
| Melting Point ¹⁾ | | °C | D3418 | 151.3 |
| Glass Transition Temperature ¹⁾ | | °C | D3418 | 59.8 |
| Melt Flow Rate (190°C, 2.16Kg) | | g/10 min | D1238 | 4.6 |
| Tensile Strength at Break ²⁾ | MD | MPa | D882 | 42 |
| | TD | | | 39 |
| Elongation at Break ²⁾ | MD | % | | 300 |
| | TD | | | 300 |

1) Differential Scanning Calorimeter (DSC), peak of endotherm. Heating rate 10 $^\circ$ C/min.

2) Film specimens conforms to ASTM D882. Crosshead speed 200 mm/min for mechanical properties.

PROCESSING CONDITION FOR BLOW FILM

| Dry Temperature ¹⁾ | 60 °C X 8 hrs | Feed Throat | 20 ~ 40 °C |
|-------------------------------|---------------|---------------------|--------------|
| Feed Temperature | 100 ~ 120 °C | Compression section | 130 ~ 160 °C |
| Melt Temperature | 130 ~ 160 °C | Nozzle | 150 ~ 170 ℃ |

1) It is preferable to dry with air below -40°C dew point.

CJ Biomaterials Inc. makes no warranty, express or implied, regarding the information contained herein or its products,

including but not limited to any warranty as to the accuracy or completeness of information,

or any implied warranty of merchantability or fitness for a particular purpose.

The content of this document is subject to change without notice.



